NC/QC/BD/2020-21/RSC-CB5A

Date: 17-07-2020

1. TEST REPORT ON CEMENT CONCRETE CUBES:

Sub: Testing of Concrete Cubes (for 28days Compressive Strength).
{Project*: Improvements to CC Roads and RCC Drains at Right Side Cross Roads of 2nd Main Road Kuvempu Nagara, and Surrounding area in Ward No.05.}
Ref.: Material testing/PMC/20-21,
Report Required for: Assistant Executive Engineer,
Byatarayanapura Sub Division,
BBMP, Bangalore.
Name of the Agency/Contractor*: M/s KRIDL, Bangalore.

RESULTS OF COMPRESSIVE STRENGTH ON CEMENT CONCRETE CUBE SPECIMENS

Dimensions of Specimen : 150 X 150 X 150mm
Grade of Concrete* : M_{20}

TABLE 1.1:

Sl No	Location/ Identification*	Date of Casting*	Date of Testing	Age in Days	C/S Area in mm^2	Maximum Load in K.N	Compressive Strength (N/mm^2)	Avg. Value
1	001	19-06-20	17-07-20	28	22500	510	22.67	22.37
	002	"	"	"	"	495	22.00	
	003	"	"	"	"	505	22.44	

Page No. 1/1,

For Newzen Consultants Bangalore

Director

ಸಹಾಯಕ ಕಾರ್ಯನಿರ್ವಾಹಕ ಅಭಿಯಂತರರು
ಬ್ಯಾಟರಾಯನಪುರ ಉಪ ವಿಭಾಗ
ಬಿ.ಬಿ.ಎಂ.ಪಿ., ಬೆಂಗಳೂರು-24

Scanned with CamScanner

NC/QC/BD/2020-21/RSC-CB6A

Date: 18-07-2020

1. TEST REPORT ON CEMENT CONCRETE CUBES:

Sub: Testing of Concrete Cubes (for 28days Compressive Strength).
{Project*: Improvements to CC Roads and RCC Drains at Right Side Cross Roads of 2nd Main Road Kuvempu Nagara, and Surrounding area in Ward No.05.}
Ref.: Material testing/PMC/20-21,
Report Required for: Assistant Executive Engineer,
Byatarayanapura Sub Division,
BBMP, Bangalore.
Name of the Agency/Contractor*: M/s KRIDL, Bangalore.

RESULTS OF COMPRESSIVE STRENGTH ON CEMENT CONCRETE CUBE SPECIMENS

Dimensions of Specimen : 150 X 150 X 150mm
Grade of Concrete* : M_{20}

TABLE 1.1:

Sl No	Location/ Identification*	Date of Casting*	Date of Testing	Age in Days	C/S Area in mm^2	Maximum Load in K.N	Compressive Strength (N/mm^2)	Avg. Value
1	001	20-06-20	18-07-20	28	22500	525	23.33	**22.96**
	002	"	"	"	"	515	22.89	
	003	"	"	"	"	510	22.67	

Page No. 1/1,

For Newzen Consultants Bangalore
Director

Scanned with CamScanner

NC/QC/BD/2020-21/RSC-W1 Date: 30-06-2020

TEST REPORT ON WET MIX MACADAM MIX

(GRADATION TEST)

Sub: To conduct Gradation test on Wet Mix Macadam (WMM) Mix.
{Project*: Improvements to CC Roads and RCC Drains at Right Side Cross Roads of 2nd Main Road Kuvempu Nagara, and Surrounding area in Ward No.05.}
Ref.: Material testing/PMC/20-21,
Report Required for: Assistant Executive Engineer,
Byatarayanapura Sub Division,
BBMP, Bangalore.
Name of the Agency/Contractor*: M/s KRIDL, Bangalore.

TEST RESULTS

1. Gradation Test:

TABLE 1.1

Sieve Size mm	Percent by Weight passing the Sieve from the sample supplied (Obtained Gradation)	Specified Limits as per MoRTH Specifications, V Revision-2013
53.00	**100.00**	100
45.00	**97.45**	95-100
26.50	**---**	-
22.40	**71.25**	60-80
11.20	**54.90**	40-60
4.75	**31.65**	25-40
2.36	**24.10**	15-30
0.600	**19.05**	8-22
0.075	**3.80**	0-5

For Newzen Consultants Bangalore
Proprietor

ಸಹಾಯಕ ಕಾರ್ಯಪಾಲಕ ಅಧಿಕಾರಿಯವರು
ಬ್ಯಾಟರಾಯನಪುರ ಉಪ ವಿಭಾಗ
ಬಿ.ಬಿ.ಎಂ.ಪಿ., ಬೆಂಗಳೂರು-24

NEWZEN CONSULTANT BANGALORE, #13,10TH MAIN ROAD 2ND CROSS JNANAJYOTHI NAGARA, JNANABHARATHI, BANGALORE-560056. CELL NO: +91 8792620231, 080 23240187
EMAIL:newzen576@gmail.com

Scanned with CamScanner

Date: 30-06-2020

TABLE 1.2

SL No	Test conducted	Test Results	Tests Conforms to IS 2386(Part I to IV)– 1963 (Reaffirmed on 2002) & Requirements as per IS:383-1970 & M.o.R.T.H Specification, V Revision -2013.
1.	Aggregate Impact Value	**27.56%**	Not more than 30.00 %
2.	Combined Flakiness and Elongation index, %	**28.39%**	Not more than 35.0 %
3.	Water absorption, %	**0.42 %**	Not more than 2.0 %
4.	Plasticity Index, %	**NP**	Not more than 6.0 %

For Newzen Consultants Bangalore

Proprietor

ಸಹಾಯಕ ಕಾರ್ಯಪಾಲಕ ಅಭಿಯಂತರರು
ಬ್ಯಾಟರಾಯನಪುರ ಉಪ ವಿಭಾಗ
ಬಿ.ಬಿ.ಎಂ.ಪಿ., ಬೆಂಗಳೂರು-24

Scanned with CamScanner

NC/QC/BD/2020-21/RSC-C3 Date: 03-07-2020

1. TEST REPORT ON CEMENT:

Sub: Testing of 53 Grade Cement Sample (IS 12269-1987).
{Project*: Improvements to CC Roads and RCC Drains at Right Side Cross Roads of 2nd Main Road Kuvempu Nagara, and Surrounding area in Ward No.05.}
Ref.: Material testing/PMC/20-21,
Report Required for: Assistant Executive Engineer,
Byatarayanapura Sub Division,
BBMP, Bangalore.
Name of the Agency/Contractor*: M/s KRIDL, Bangalore.

PHYSICAL TESTS ON CEMENT

Grade * : 53,
Type * : O.P.C

TABLE 1.1:

SL No	Name of Test	Test Results	Requirements as per IS 8112-1989
1	Initial setting time	**152 min**	Shall not be less than 30 min
2	Final setting time	**265min**	Shall not be more than 600 min
3	Fineness (by dry sieving on IS 90 micron sieve)	**2.15%**	Not to exceed 10.0%
4	Soundness test(by Le-Chatelier's method)	**2.09 mm**	Shall not be more than 10 mm
5	Compressive strength b) 3 days (average of three results)	**28.76 N/Sq mm**	Shall not be less than 27 N/Sqmm

For Newzen Consultants Bangalore
Proprietor

ಸಹಾಯಕ ಕಾರ್ಯನಿರ್ವಾಹಕ ಅಭಿಯಂತರರು
ಬ್ಯಾಟರಾಯನಪುರ ಉಪ ವಿಭಾಗ
ಬಿ.ಬಿ.ಎಂ.ಪಿ., ಬೆಂಗಳೂರು-24

NEWZEN CONSULTANT BANGALORE, #13,10TH MAIN ROAD 2ND CROSS JNANAJYOTHI NAGARA,
JNANABHARATHI, BANGALORE-560056. CELL NO: +91 8792620231, 080 23240187
EMAIL:newzen576@gmail.com

Scanned with CamScanner

NC/QC/BD/2020-21/RSC-PCC2 Date: 03-07-2020

1. TESTING OF COARSE AND FINE AGGREGATES:

Sub: Testing of Coarse and Fine aggregates to be used for bed concrete.
{Project*: Improvements to CC Roads and RCC Drains at Right Side Cross Roads of 2nd Main Road Kuvempu Nagara, and Surrounding area in Ward No.05.}
Ref.: Material testing/PMC/20-21,
Report Required for: Assistant Executive Engineer,
Byatarayanapura Sub Division,
BBMP, Bangalore.
Name of the Agency/Contractor*: M/s KRIDL, Bangalore.

1. COARSE AGGRGATES TABLE - SIEVE ANALYSIS:

IS Sieve Size, mm	Percentage passing	Requirements as per IS 383-1970 (Reaffirmed on 2007) % Passing	
	40 mm Sample	Single size	Graded
40mm	100.00	85-100	90 – 100
20mm	66.35	0 -20	30- 70
10mm	28.75	0 -5	10- 35
4.75mm	3.90	——	0- 5

2. FINE AGGREGATES TABLE - SIEVE ANALYSIS:

IS Sieve Size, mm	Percentage Passing	Specification as Per IS: 383-1970(Reaffirmed 2002) Percentage Passing			Remarks
		Zone-I	Zone-II	Zone -III	
04.75	96.15	90-100	90-100	90-100	The Sample Conforms to Grading Zone-II
02.36	83.05	60-95	75-100	85-100	
01.18	75.65	30-70	55-90	75-100	
600.mic	48.25	15-34	35-59	60-79	
300.mic	23.55	5-20	8-30	12-40	
150.mic	7.90	0-10	0-10	0-10	

ಸಹಾಯಕ ಕಾರ್ಯನಿರ್ವಾಹಕ ಅಭಿಯಂತರರು
ಬ್ಯಾಟರಾಯನಪುರ ಉಪ ವಿಭಾಗ

Page No. 1/1,

ಸಹಾಯಕ ಕಾರ್ಯನಿರ್ವಾಹಕ ಅಭಿಯಂತರರು
ಬ್ಯಾಟರಾಯನಪುರ ಉಪ ವಿಭಾಗ
ಬಿ.ಬಿ.ಎಂ.ಪಿ, ಬೆಂಗಳೂರು-24

For Newzen Consultants Bangalore
Proprietor

Scanned with CamScanner

NC/QC/BD/2020-21/RSC-C4 Date: 06-07-2020

1. TEST REPORT ON CEMENT:

Sub: Testing of 53 Grade Cement Sample (IS 12269-1987).
{Project*: Improvements to CC Roads and RCC Drains at Right Side Cross Roads of 2nd Main Road Kuvempu Nagara, and Surrounding area in Ward No.05.}
Ref.: Material testing/PMC/20-21,
Report Required for: Assistant Executive Engineer,
Byatarayanapura Sub Division,
BBMP, Bangalore.
Name of the Agency/Contractor*: M/s KRIDL, Bangalore.

PHYSICAL TESTS ON CEMENT

Grade * : 53,
Type * : O.P.C

TABLE 1.1:

SL No	Name of Test	Test Results	Requirements as per IS 8112-1989
1	Initial setting time	**164 min**	Shall not be less than 30 min
2	Final setting time	**270 min**	Shall not be more than 600 min
3	Fineness (by dry sieving on IS 90 micron sieve)	**2.13%**	Not to exceed 10.0%
4	Soundness test(by Le-Chatelier's method)	**2.06mm**	Shall not be more than 10 mm
5	Compressive strength c) 3 days (average of three results)	**28.65 N/Sq mm**	Shall not be less than 27 N/Sqmm

Page No. 1/1,

For Newzen Consultants Bangalore
Proprietor

Scanned with CamScanner

NC/QC/BD/2020-21/RSC-PCC3 Date: 06-07-2020

1. TESTING OF COARSE AND FINE AGGREGATES:

Sub: Testing of Coarse and Fine aggregates to be used for bed concrete.
{Project*: Improvements to CC Roads and RCC Drains at Right Side Cross Roads of 2nd Main Road Kuvempu Nagara, and Surrounding area in Ward No.05.}
Ref.: Material testing/PMC/20-21,
Report Required for: Assistant Executive Engineer,
Byatarayanapura Sub Division,
BBMP, Bangalore.
Name of the Agency/Contractor*: M/s KRIDL, Bangalore.

1. COARSE AGGRGATES TABLE - SIEVE ANALYSIS:

IS Sieve Size, mm	Percentage passing	Requirements as per IS 383-1970 (Reaffirmed on 2007) % Passing	
	40 mm Sample	Single size	Graded
40mm	100.00	85-100	90 – 100
20mm	64.25	0 -20	30- 70
10mm	31.55	0 -5	10- 35
4.75mm	4.10	------	0- 5

2. FINE AGGREGATES TABLE - SIEVE ANALYSIS:

IS Sieve Size, mm	Percentage Passing	Specification as Per IS: 383-1970(Reaffirmed 2002) Percentage Passing			Remarks
		Zone-I	Zone-II	Zone -III	
04.75	97.65	90-100	90-100	90-100	The Sample Conforms to Grading **Zone-II**
02.36	81.05	60-95	75-100	85-100	
01.18	74.15	30-70	55-90	75-100	
600.mic	48.35	15-34	35-59	60-79	
300.mic	25.10	5-20	8-30	12-40	
150.mic	6.90	0-10	0-10	0-10	

ಸಹಾಯಕ ಅಭಿಯಂತರರು
ಬಿ.ಬಿ.ಎಂ.ಪಿ. ಬ್ಯಾಟರಾಯನಪುರ ಉಪ ವಿಭಾಗ

ಸಹಾಯಕ ಕಾರ್ಯ[illegible]
ಬ್ಯಾಟರಾಯನಪುರ ಉಪ ವಿಭಾಗ
ಬಿ.ಬಿ.ಎಂ.ಪಿ., ಬೆಂಗಳೂರು-24

For Newzen Consultants Bangalore
Proprietor

NEWZEN CONSULTANT BANGALORE, #13,10TH MAIN ROAD 2ND CROSS JNANAJYOTHI NAGARA,
JNANABHARATHI, BANGALORE-560056. CELL NO: +91 8792620231, 080 23240187
EMAIL:newzen576@gmail.com

Scanned with CamScanner

NC/QC/BD/2020-21/RSC-CB7 Date: 17-07-2020

1. TEST REPORT ON CEMENT CONCRETE CUBES:

Sub: Testing of Concrete Cubes (for 07days Compressive Strength).
{Project*: Improvements to CC Roads and RCC Drains at Right Side Cross Roads of 2nd Main Road Kuvempu Nagara, and Surrounding area in Ward No.05.}
Ref.: Material testing/PMC/20-21,
Report Required for: Assistant Executive Engineer,
Byatarayanapura Sub Division,
BBMP, Bangalore.
Name of the Agency/Contractor*: M/s KRIDL, Bangalore.

RESULTS OF COMPRESSIVE STRENGTH ON CEMENT CONCRETE CUBE SPECIMENS

Dimensions of Specimen : 150 X 150 X 150mm
Grade of Concrete* : M_{30}

TABLE 1.1:

Sl No	Location/ Identification*	Date of Casting*	Date of Testing	Age in Days	C/S Area in mm^2	Maximum Load in K.N	Compressive Strength (N/mm^2)	Avg. Value
1	001	10-07-20	17-07-20	07	22500	515	22.89	23.41
	002	"	"	"	"	540	24.00	
	003	"	"	"	"	525	23.33	

For Newzen Consultants Bangalore
Director

NEWZEN CONSULTANT BANGALORE, #13,10TH MAIN ROAD 2ND CROSS JNANAJYOTHI NAGARA,
JNANABHARATHI, BANGALORE-560056. CELL NO: +91 8792620231, 080 23240187
EMAIL:newzen576@gmail.com

Scanned with CamScanner

NC/QC/BD/2020-21/RSC-CB8 Date: 20-07-2020

1. TEST REPORT ON CEMENT CONCRETE CUBES:

Sub: Testing of Concrete Cubes (for 07days Compressive Strength).
{Project*: Improvements to CC Roads and RCC Drains at Right Side Cross Roads of 2nd Main Road Kuvempu Nagara, and Surrounding area in Ward No.05.}
Ref.: Material testing/PMC/20-21,
Report Required for: Assistant Executive Engineer,
Byatarayanapura Sub Division,
BBMP, Bangalore.
Name of the Agency/Contractor*: M/s KRIDL, Bangalore.

RESULTS OF COMPRESSIVE STRENGTH ON CEMENT CONCRETE

CUBE SPECIMENS

Dimensions of Specimen : 150 X 150 X 150mm
Grade of Concrete* : M_{30}

TABLE 1.1:

Sl No	Location/ Identification*	Date of Casting*	Date of Testing	Age in Days	C/S Area in mm^2	Maximum Load in K.N	Compressive Strength (N/mm^2)	Avg. Value
1	001	13-07-20	20-07-20	07	22500	530	23.56	**23.70**
	002	‘’	“	‘’	“	525	23.33	
	003	‘’	“	‘’	“	545	24.22	

For Newzen Consultants Bangalore
Proprietor

ಸಹಾಯಕ ಅಭಿಯಂತರರು
ಬಿ.ಬಿ.ಎಂ.ಪಿ ಬ್ಯಾಟರಾಯನಪುರ ಉಪ ವಿಭಾಗ

ಸಹಾಯಕ ಕಾರ್ಯಪಾಲಕ ಅಭಿಯಂತರರು
ಬ್ಯಾಟರಾಯನಪುರ ಉಪ ವಿಭಾಗ
ಬಿ.ಬಿ.ಎಂ.ಪಿ., ಬೆಂಗಳೂರು-24.

NEWZEN CONSULTANT BANGALORE, #13,10TH MAIN ROAD 2ND CROSS JNANAJYOTHI NAGARA,
JNANABHARATHI, BANGALORE-560056. CELL NO: +91 8792620231, 080 23240187
EMAIL:newzen576@gmail.com

Scanned with CamScanner

NC/QC/BD/2020-21/RSC-CB9

Date: 20-07-2020

1. TEST REPORT ON CEMENT CONCRETE CUBES:

Sub: Testing of Concrete Cubes (for 07days Compressive Strength).
{Project*: Improvements to CC Roads and RCC Drains at Right Side Cross Roads of 2nd Main Road Kuvempu Nagara, and Surrounding area in Ward No.05.}
Ref.: Material testing/PMC/20-21,
Report Required for: Assistant Executive Engineer,
Byatarayanapura Sub Division,
BBMP, Bangalore.
Name of the Agency/Contractor*: M/s KRIDL, Bangalore.

RESULTS OF COMPRESSIVE STRENGTH ON CEMENT CONCRETE CUBE SPECIMENS

Dimensions of Specimen : 150 X 150 X 150mm

Grade of Concrete* : M_{30}

TABLE 1.1:

Sl No	Location/ Identification*	Date of Casting*	Date of Testing	Age in Days	C/S Area in mm^2	Maximum Load in K.N	Compressive Strength (N/mm^2)	Avg. Value
1	001	13-07-20	20-07-20	07	22500	530	23.56	**23.33**
	002	‘’	“	‘’	“	530	23.56	
	003	‘’	“	‘’	“	515	22.89	

For Newzen Consultants Bangalore
Proprietor

ಸಹಾಯಕ ಕಾರ್ಯಪಾಲಕ ಅಭಿಯಂತರರು
ಬಿ.ಬಿ.ಎಂ.ಪಿ ಬ್ಯಾಟರಾಯನಪುರ ಉಪ ವಿಭಾಗ

ಸಹಾಯಕ ಕಾರ್ಯಪಾಲಕ ಅಭಿಯಂತರರು
ಬ್ಯಾಟರಾಯನಪುರ ಉಪ ವಿಭಾಗ
ಬಿ.ಬಿ.ಎಂ.ಪಿ., ಬೆಂಗಳೂರು-24

NEWZEN CONSULTANT BANGALORE, #13,10TH MAIN ROAD 2ND CROSS JNANAJYOTHI NAGARA,
JNANABHARATHI, BANGALORE-560056. CELL NO: +91 8792620231, 080 23240187
EMAIL:newzen576@gmail.com

Scanned with CamScanner

NC/QC/BD/2020-21/RSC-CB7A

Date: 07-08-2020

1. TEST REPORT ON CEMENT CONCRETE CUBES:

Sub: Testing of Concrete Cubes (for 28days Compressive Strength).
{Project*: Improvements to CC Roads and RCC Drains at Right Side Cross Roads of 2nd Main Road Kuvempu Nagara, and Surrounding area in Ward No.05.}
Ref.: Material testing/PMC/20-21,
Report Required for: Assistant Executive Engineer,
Byatarayanapura Sub Division,
BBMP, Bangalore.
Name of the Agency/Contractor*: M/s KRIDL, Bangalore.

RESULTS OF COMPRESSIVE STRENGTH ON CEMENT CONCRETE

CUBE SPECIMENS

Dimensions of Specimen : 150 X 150 X 150mm

Grade of Concrete* : M_{30}

TABLE 1.1:

Sl No	Location/ Identification*	Date of Casting*	Date of Testing	Age in Days	C/S Area in mm^2	Maximum Load in K.N	Compressive Strength (N/mm^2)	Avg. Value
1	001	10-07-20	07-08-20	28	22500	740	32.89	**32.44**
	002	"	"	"	"	730	32.44	
	003	"	"	"	"	720	32.00	

For Newzen Consultants Bangalore

Proprietor

ಸಹಾಯಕ ಕಾರ್ಯಪಾಲಕ ಅಭಿಯಂತರರು
ಬ್ಯಾಟರಾಯನಪುರ ಉಪ ವಿಭಾಗ
ಬಿ.ಬಿ.ಎಂ.ಪಿ., ಬೆಂಗಳೂರು-24

ಸಹಾಯಕ ಕಾರ್ಯಪಾಲಕ ಅಭಿಯಂತರರು
ಬ್ಯಾಟರಾಯನಪುರ ಉಪ ವಿಭಾಗ
ಬಿ.ಬಿ.ಎಂ.ಪಿ.

Scanned with CamScanner

NC/QC/BD/2020-21/RSC-CB8A **Date: 10-08-2020**

1. TEST REPORT ON CEMENT CONCRETE CUBES:

Sub: Testing of Concrete Cubes (for 28days Compressive Strength).
{Project*: Improvements to CC Roads and RCC Drains at Right Side Cross Roads of 2nd Main Road Kuvempu Nagara, and Surrounding area in Ward No.05.}
Ref.: Material testing/PMC/20-21,
Report Required for: Assistant Executive Engineer,
Byatarayanapura Sub Division,
BBMP, Bangalore.
Name of the Agency/Contractor*: M/s KRIDL, Bangalore.

RESULTS OF COMPRESSIVE STRENGTH ON CEMENT CONCRETE CUBE SPECIMENS

Dimensions of Specimen : 150 X 150 X 150mm

Grade of Concrete* : M_{30}

TABLE 1.1:

Sl No	Location/ Identification*	Date of Casting*	Date of Testing	Age in Days	C/S Area in mm^2	Maximum Load in K.N	Compressive Strength (N/mm^2)	Avg. Value
1	001	13-07-20	10-08-20	28	22500	730	32.44	**32.81**
	002	"	"	"	"	745	33.11	
	003	"	"	"	"	740	32.89	

For Newzen Consultants Bangalore
Proprietor

ಸಹಾಯಕ ಅಧಿಕಾರಿಯವರು
ಬಿ.ಬಿ.ಎಂ.ಪಿ ಬ್ಯಾಟರಾಯನಪುರ ಉಪ ವಿಭಾಗ

ಸಹಾಯಕ ಕಾರ್ಯಪಾಲಕ ಅಭಿಯಂತರರು
ಬ್ಯಾಟರಾಯನಪುರ ಉಪ ವಿಭಾಗ
ಬಿ.ಬಿ.ಎಂ.ಪಿ., ಬೆಂಗಳೂರು-24

NEWZEN CONSULTANT BANGALORE, #13,10TH MAIN ROAD 2ND CROSS JNANAJYOTHI NAGARA,
JNANABHARATHI, BANGALORE-560056. CELL NO: +91 8792620231, 080 23240187
EMAIL:newzen576@gmail.com

Scanned with CamScanner

NC/QC/BD/2020-21/RSC-CB9A

Date: 10-08-2020

1. TEST REPORT ON CEMENT CONCRETE CUBES:

Sub: Testing of Concrete Cubes (for 28days Compressive Strength).
{Project*: Improvements to CC Roads and RCC Drains at Right Side Cross Roads of 2nd Main Road Kuvempu Nagara, and Surrounding area in Ward No.05.}
Ref.: Material testing/PMC/20-21,
Report Required for: Assistant Executive Engineer,
Byatarayanapura Sub Division,
BBMP, Bangalore.
Name of the Agency/Contractor*: M/s KRIDL, Bangalore.

RESULTS OF COMPRESSIVE STRENGTH ON CEMENT CONCRETE CUBE SPECIMENS

Dimensions of Specimen : 150 X 150 X 150mm

Grade of Concrete* : M_{30}

TABLE 1.1:

Sl No	Location/ Identification*	Date of Casting*	Date of Testing	Age in Days	C/S Area in mm^2	Maximum Load in K.N	Compressive Strength (N/mm^2)	Avg. Value
1	001	13-07-20	10-08-20	28	22500	730	32.44	**32.37**
	002	"	"	"	"	740	32.89	
	003	"	"	"	"	715	31.78	

For Newzen Consultants Bangalore
Director

ಸಹಾಯಕ ಕಾರ್ಯನಿರ್ವಾಹಕ ಅಭಿಯಂತರರು
ಬ್ಯಾಟರಾಯನಪುರ ಉಪ ವಿಭಾಗ
ಬಿ.ಬಿ.ಎಂ.ಪಿ., ಬೆಂಗಳೂರು-24

NEWZEN CONSULTANT BANGALORE, #13,10TH MAIN ROAD 2ND CROSS JNANAJYOTHI NAGARA, JNANABHARATHI, BANGALORE-560056. CELL NO: +91 8792620231, 080 23240187
EMAIL:newzen576@gmail.com

Scanned with CamScanner